




Features

- Reduces Bus Bar clearance
- Protects against accidental flash-over
- Anti Tracking
- Halogen Free
- Continuous Operating Temperature: -40°C to +135°C
- Shrink temperature: 125°C

ORDER REF. NO.	EXPANDED		RECOVERED	
	INTERNAL DIAMETER D (MIN)	INTERNAL DIAMETER d (MAX)	WALL THICKNESS W (NOM)	STANDARD LENGTHS
ATBB	mm	mm	mm	m
19/6	19.0	6.0	2.00	50
25/10	25.0	10.0	4.10	50
32/12	32.0	12.0	2.80	50
38/12	38.0	12.0	2.80	25
45/16	45.0	16.0	4.10	25
58/19	58.0	19.0	3.50	25
68/25	68.0	25.0	3.50	25
76/32	76.0	32.0	3.50	15
90/32	90.0	32.0	3.50	15
100/40	100.0	40.0	4.10	10

Other sizes & wall thickness may be available on request



Properties	Test Method	Performance
Specific gravity	ASTM-D792,A-I	1.2g/cm ³ max.
Tensile strength	IEC 60684-2	14 MPa
Ultimate elongation	IEC 60684-2	500%
Longitudinal Change	ASTM-D 2671	6% ± 3% max
Secant Modulus	ASTM-D 882	30 Mpa max.
Low Temperature flexibility	ASTM-D 2671 Meth C	Does not break at -40degC
Flamability	FMVSS 302	passed
Electrical Properties		
Dielectric strength	VDE 0303 Part 2	min 20 kV/mm
Volume Resistivity	VDE 0303 Part 2	10 E14 ohm/cm
Comparative Tracking Index	IEC 112	CTI 600<0.1
Chemical Properties:		
Water absorption	VDE 0472	0.20%
Corrosive Action	ASTM-D 2671 A	non corrosive
Copper compatibility	ASTM-D 2671 B	non corrosive

All information contained in this leaflet is believed to be reliable. We advise however that customers should separately evaluate the suitability of the products for their particular application. Heatshrink Solutions Limited give no guarantees in respect of the accuracy or sufficiency of the information presented and disclaim any liability regarding its use. In no instance will we be liable for any eventual, indirect, or consequential damage or damages arising from the sale, resale, transfer, use or misuse of the product.

STANDARD COLOURS

Red - Brown



Special colours not available.