


## Medium Wall Corrosion Protection Tubes

# CPT




CPT is a mastic lined heat shrinkable tubing designed specifically for protection of metal pipe joints, or similar connections requiring environmental sealing.

The radiation cross linked jacket provides effective mechanical protection, whilst the mastic layer resists water & moisture access.

## Features

- UV Resistant
- 3:1 Shrink Ratio
- Continuous Operating Temperature: -35°C to +110°C (Jacket only)
- Shrink temperature: 120°C



STANDARD COLOURS
black

ORDER REF. NO.	EXPANDED		RECOVERED		STANDARD LENGTHS *
	INTERNAL DIAMETER D (MIN)	INTERNAL DIAMETER d (MAX)	INTERNAL DIAMETER d (MAX)	WALL THICKNESS W (NOM)	
CPT	mm	mm	mm	mm	m
30/10	30	10	2.5	2.5	1.22
33/11	33	11	2.5	2.5	1.22
40/13	40	13	2.5	2.5	1.22
45/15	45	15	2.5	2.5	1.22
55/16	55	16	2.7	2.7	1.22
75/25	75	25	3.0	3.0	1.22
90/30	90	30	3.0	3.0	1.22
120/40	120	40	3.0	3.0	1.22
130/42	130	42	3.0	3.0	1.22
140/45	140	45	3.0	3.0	1.22
160/50	160	50	3.0	3.0	1.22
180/60	180	60	3.0	3.0	1.22
205/70	205	70	3.0	3.0	1.22
235/80	235	80	3.0	3.0	1.22
265/85	260	85	3.0	3.0	1.22
300/100	300	100	3.0	3.0	1.22

\* Other SIZES & lengths available on request

Tube Properties	Test Method	Performance (Typical)
Operating Temperature	IEC 216	-35°C to +110°C
Tensile strength	ASTM D 638	14 MPa
Ultimate elongation	ASTM D 638	> 400%
Longitudinal Change	UL 224	+0 to -10%
Dielectric strength	IEC 243	>20 kV/mm
Volume Resistance	IEC 93	10 <sup>14</sup> Ohm-cm
Eccentricity	ASTM D 2671	< 30%
Copper Stability	ASTM-D 2671	Pass
Adhesive Properties		
Water Absorption	ISO 62	< 0.1%
Softening Point	ASTM D E28	80°C
Peel Strength	DIN 30672	50N/25mm
Copper Stability	ASTM D 2671	Non corrosive
Resistance to fungus	ISO 846	Pass

All information contained in this leaflet is believed to be reliable. We advise however that customers should separately evaluate the suitability of the products for their particular application. Heatshrink Solutions Limited give no guarantees in respect of the accuracy or sufficiency of the information presented and disclaim any liability regarding its use. In no instance will we be liable for any eventual, indirect, or consequential damage or damages arising from the sale, resale, transfer, use or misuse of the product.