


Heavy Wall Crosslinked Polyolefin



Features

- Heavy Wall tubes
- High Resistance to Impact and Abrasion
- 3:1 Shrink Ratio
- Continuous Operating Temperature: -55°C to +110°C
- Shrink temperature: 120°C



PRODUCT DIMENSIONS (mm)

HWA tubes are internally coated with a film lining of Hot Melt Adhesive. If this coating is not required then use reference HW only.

ORDER REF. NO.	EXPANDED		RECOVERED	
	INTERNAL DIAMETER	INTERNAL DIAMETER	WALL THICKNESS W	STANDARD LENGTHS *
HW HWA	mm	mm	mm	m
9/3	9	3	2.0	1.2
13/4	13	4	2.5	1.2
22/6	22	6	2.7	1.2
33/8	33	8	3.2	1.2
40/12	40	12	4.1	1.2
45/12	45	12	4.1	1.2
55/16	55	16	4.1	1.2
75/22	75	22	4.1	1.2
85/25	85	25	4.1	1.2
95/29	95	29	4.1	1.2
115/34	115	34	4.3	1.2
130/36	130	36	4.3	1.2
160/55	160	55	4.3	1.2
175/55	175	55	4.3	1.2
200/65	200	65	4.3	1.2

* Other sizes & lengths available on request

Adhesive		
Copper Stability	ASTM-D-2671	Non Corrosive
Water absorption	ASTM D- 570	0.10%
Fungus Resistance	ISO 846	Pass
Adhesive Softening Point	ASTM D E8	80°C
Adhesive Peel Strength	DIN 30672	4N/cm

Property	Test Method	Performance
Resistance to stress	ASTM D- 1693	No Cracking
Longitudinal Change	UI 224	0%,-10%
Tensile strength	ASTM D 638	>14.MPa
Ultimate elongation	ASTM-D 638	>400%
Elongation after Ageing	(168hrs)	>300%
Eccentricity	ASTM D 792	<30%
Density	ASTM-D 792	1.05 g/cm ³
Dielectric strength	IEC 243	>20kV/mm
Volume resistance	IEC 93	10 ¹⁴ Ohm-cm
Water Absorption	ISO 62	<0.15%

STANDARD COLOURS
black ●
Special colours available on request

All information contained in this leaflet is believed to be reliable. We advise however that customers should separately evaluate the suitability of the products for their particular application. Heatshrink Solutions Limited give no guarantees in respect of the accuracy or sufficiency of the information presented and disclaim any liability regarding its use. In no instance will we be liable for any eventual, indirect, or consequential damage or damages arising from the sale, resale, transfer, use or misuse of the product.